

THERMALLY INSULATING PANEL



LABARA

High-strength, temperature resistant insulation made from glass fibre reinforced composite materials



They play a very important role in accurate temperature controls and energy conservation.



They are employed wherever thermal separation is required for operational and/or economic reasons between components in installations..

LABARA



**THESE ALL OFFER
THE FOLLOWING
SPECIAL
CHARACTERISTICS:**

LABARA

GLASTHERM HT 200 ❖ max. continuous operating temperature 200°C ❖ measurements: 1255x2455 mm 918x1828 mm	GLASTHERM HT 220 ❖ max. continuous operating temperature 220°C ❖ measurements: 1220x2440 mm 1000x1900 mm	GLASTHERM HT 250 M ❖ max. continuous operating temperature 250°C ❖ compressive strength 445 Mpa ❖ measurements: 1100x2000 mm 1100x3000 mm
GLASTHERM HT 250 HQ ❖ max. continuous operating temperature 250°C ❖ compressive strength 510 Mpa ❖ measurements: 1120x2000 mm 1120x3000 mm	GLASTHERM HT 300 ❖ max. continuous operating temperature 300°C ❖ measurements: 1070x1240 mm 1240x2800 mm	GLASTHERM HT 500 ❖ max. continuous operating temperature 500°C ❖ measurements: 1000x1200 mm

Mechanical properties			Glashterm® HT LC	Glashterm® HT 200	Glashterm® HT 220	Glashterm® HT 250M	Glashterm® HT 250HQ	Glashterm® HT 300	Glashterm® HT 500	
	Test method	Unit	Guideline value	Guideline value	Guideline value	Guideline value	Guideline value	Guideline value	Guideline value	
	ISO 1183	g / cm3	1,5	1,9	1,85	2,00	2,00	1,90	2,15	
	ISO 178	MPa	170	200	360	300	600	120	165	
	ISO 178	MPa	10000	12000	18000	22000	30000	15000	-	
	ISO 604	MPa	300	320	500	600	700	330	400	
	ISO 604	MPa	90	230	360	445	510	280	250	
	ISO 527	MPa	-	120	280	250	400	-	150	
	ISO 179	kJ / m2	80	100	150	150	300	-	-	
Splitting force II		DIN 53463	N	-	2200	4000	5000	-	-	-
Thermal properties										
Thermal conductivity 2) ⊥			W / (m * K)	0,18	≈ 0,3	≈ 0,25	≈ 0,23	≈ 0,27	≈ 0,28	≈ 0,25
Coefficient of linear expansion II		TMA (Mettler)	10-6 x K-1	≈ 20	≈ 20	≈ 10 - 15	10 - 15	≈ 10 - 15	≈ 10 - 15	≈ 10
Max. continuous operating temperature			°C	200	200	220	250	250	300	500

DELTERM 68330 (HT 200) ❖ maximum heat resistance (for short periods) 200°C ❖ measurements: 1000x2000 mm	DELTERM 68890 (HT 220) ❖ maximum heat resistance (for short periods) 280°C ❖ measurements: 1335x2350 mm 1335x2950 mm	DELTERM 68990 (HT 250M) ❖ maximum heat resistance (for short periods) 300°C ❖ measurements: 1335x2950 mm
CETHERM 65100 ❖ maximum heat resistance (for short periods) 900°C ❖ measurements: 910x1220 mm	Mica 41130 ❖ maximum heat resistance (for short periods) 900°C ❖ measurements: 1000x1200 mm	Mica 41140 ❖ maximum heat resistance (for short periods) 700°C ❖ measurements: 1000x1200 mm

			Deltherm 68330	Deltherm 68990	Deltherm MT 68110	Lightherm 68880	Deltherm 68890	Cetherm 65100	Mica 41130	Mica 41140
	Test Method	Jednotka	Value	Value	Value	Value	Value	Value	Value	Value
Physical Properties										
Density	ISO 1183 (Method A)	g / cm3	1,9±0,1	1,9±0,1	1,9±0,1	1,4±0,1	1,9±0,1	1,75±0,1	2,15±0,1	2,15±0,1
Water absorption (24h 23°C)	ISO 62 (Method 1)	%	0,1	0,08	0,1	0,15	0,08	15	0,15	0,15
Hořlavost	UL 94		x	x	x	x	x	x	V-0	V-0
Thermal Properties										
Maximum heat resistance (for short periods)		°C	200	300	200	240	280	900	900	700
Heat resistance		°C	180	240	180	200	240	500	700	500
Coefficient of linear expansion //	VSM77110	K ⁻¹	20.10 ⁻⁶	15.10 ⁻⁶	20.10 ⁻⁶	x	15	10.10 ⁻⁶	10	x
Coefficient of linear expansion //		1,0 ⁻⁶ /K	x	x	x	x	x	x	10	10
Thermal conductivity	IEC 60893	W/m.K	0,27	0,3	0,27	0,15	0,24	0,40	0,18	0,18
Electrical Properties										
Flatwise Electric strength	IEC 60243-1	kV/mm	7	x	x	x	14	x	21	21
Flatwise Electric strength, 90° in oil	IEC 60243-1	kV/mm	x	14	x	x	x	x	x	x
⊥ Electric strength (step by step , in oil at 90°C)	IEC 60243-1	kV/mm	x	x	x	x	x	3	x	x
Mechanical Properties										
Flexural strength at 23°C, flatwise	ISO 178	MPa	160	420	130	250	420	x	100	170
Flexural strength at 155°C, flatwise	ISO 178	MPa	100	x	65	x	x	x	70	110
Flexural strength at 200°C, flatwise	ISO 178	MPa	50	x	45	x	x	x	x	x
Tensile strength at 23°C, edgewise	ISO 178	Mpa	x	x	x	x	x	x	110	150
Flatwise compressive strength, at 23°C	ISO 604	MPa	420	700	360	300	590	x	250	400
Flatwise compressive strength, at 155°C	ISO 604	MPa	200	500	140	x	450	x	140	250
Flatwise compressive strength, at 200°C	ISO 604	MPa	120	430	90	120	370	x	x	x
Flatwise compressive strength, at 250°C	ISO 604	MPa	x	350	x	x	x	x	x	x
Flexural strength at 23°C, ⊥	ISO 178	MPa	x	x	x	x	x	32	x	x
Compressive strength at 23°C, ⊥	ISO 604	MPa	x	x	x	x	x	115	x	x
Compressive strength at 200°C, ⊥	ISO 604	MPa	x	x	x	x	x	90	x	x

IF YOU HAVE ANY FURTHER
QUESTIONS, DON'T HESITATE TO
CONTACT:

František Bednář

+420 777 008 130

BEDNAR@LABARA.CZ

LABARA